



MODEL: 5SHP-GEL

VOLTAGE: 12

DIMENSIONS: Inches (mm)

BATTERY: VRLA GEL

COLOR: Maroon (case) Grey (cover)

MATERIAL: Polypropylene

WATERING SYSTEM: N/A



### PRODUCT SPECIFICATIONS

BCI GROUP SIZE	TYPE	CAPACITY Minutes	CAPACITY® Amp-Hours (AH)				ENERGY (kWh)	TERMINAL	DIMENSIONS (Inches (mm)			WEIGHT Ibs.
			5-Hr Rate	10-Hr Rate	20-Hr Rate	100-Hr Rate	100-Hr Rate	Type <sup>E</sup>	Length	Width	Height <sup>®</sup>	(kg)
					12 VOLT	DEEP CY	CLE GEL BA	TTERY				
DIN	SSHP-GEL	250	110	115	125	137	1.64	8	13.58 (345)	6.75 (172)	11.01 (280)	85 (39)

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.
- B. The amount of amp-hours (AH) a battery can deliver when discharged at a constant rate at 77°F (25°C) for Gel Lines and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.
- C. Dimensions are based on nominal size. Dimensions may vary depending on type of handle or terminal.
- D. Dimensions taken from bottom of the battery to the highest point on the battery. Heights may vary depend ing on type of terminal.
- E. Terminal images are representative only.
- Trojan's battery testing procedures adhere to both BCI and IEC test standards.

# CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
System Voltage	12V	24V	36V	48V	
Absorption Charge	14.1 - 14.4	28.2 - 28.8	42.3 – 43.2	56.4 - 57.6	
Float Charge	13.5	27	40.5	54	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

## CHARGING TEMPERATURE COMPENSATION

.028 VPC for every 10°F (5.55°C) above or below 77°F (25°C) (add .028 VPC for every 10°F (5.55°C) below 77°F and subtract .028 VPC for every 10°C above 77°F).

### **OPERATIONAL DATA**

Operating Temperature	Self Discharge			
-4°F to 113°F (-20°C to +45°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions.			

Batteries may be utilized at higher temperatures with the understanding that battery life will be reduced by 50% for every  $10^{\circ}$  C ( $18^{\circ}$  F) increase in operating temperatures over  $68^{\circ}$  F ( $20^{\circ}$  C).

#### TERMINAL CONFIGURATIONS

