

8D-GEL

Inches (mm)

Polypropylene

VRLA GEL

12

8D-GEL DATA SHEET



WATERING SYSTEM: N/A

MODEL:

VOLTAGE:

BATTERY:

MATERIAL:

COLOR:

DIMENSIONS:

PRODUCT SPECIFICATIONS

BCI GROUP	ТҮРЕ	CAPACITY ^A Minutes	CAPACITY [®] Amp-Hours (AH)				ENERGY (kWh)	TERMINAL	DIMENSIONS ^c Inches (mm)			WEIGHT lbs.
SIZE		@25 Amps	5-Hr Rate	10-Hr Rate	20-Hr Rate	100-Hr Rate	100-Hr Rate	Type ^E	Length	Width	Height ^D	(kg)
12 VOLT DEEP CYCLE GEL BATTERY												
8D	8D-GEL	500	188	207	225	265	3.18	5	20.69 (526)	10.95 (278)	10.82 (275)	168 (76)

A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.

B. The amount of amp-hours (AH) a battery can deliver when discharged at a constant rate at 80°F (27°C) and 86°F (30°C) for the 5-Hour rate and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.

C. Dimensions are based on nominal size. Dimensions may vary depending on type of handle or terminal.

D. Dimensions taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal.

Maroon (case) Grey (cover)

E. Terminal images are representative only.

Trojan's battery testing procedures adhere to both BCI and IEC test standards.

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)

System Voltage	12V	24V	36V	48V	
Absorption Charge	14.1 – 14.4	28.2 – 28.8	42.3 - 43.2	56.4 – 57.6	
Float Charge	13.5	27	40.5	54	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

.028 VPC for every 10°F (5.55°C) above or below 77°F (25°C) (add .028 VPC for every 10°F (5.55°C) below 77°F and subtract .028 VPC for every 10°C above 77°F).

OPERATIONAL DATA

Operating Temperature	Self Discharge
-4°F to 113°F (-20°C to +45°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions.


Batteries may be utilized at higher temperatures with the understanding that battery life will be reduced by 50% for every 10° C (18° F) increase in operating temperatures over 68° F (20° C).

TERMINAL CONFIGURATIONS




8D-GEL DATA SHEET


BATTERY DIMENSIONS (shown with LT)



TROJAN 8D-GEL PERFORMANCE



PERCENT CAPACITY VS. TEMPERATURE







Trojan batteries are available worldwide through Trojan's Master Distributor Network. We offer outstanding technical support, provided by full-time application engineers.

For a Trojan Master Distributor near you, call 800.423.6569 or + 1.562.236.3000 or visit www.trojanbattery.com

12380 Clark Street, Santa Fe Springs, CA 90670 • USA

© 2015 Trojan Battery Company. All rights reserved. Trojan Battery Company is not liable for damages that may result from any information provided in or omitted from this publication, under any circumstances. Trojan Battery Company reserves the right to make adjustments to this publication at any time, without notices or obligation. Please check the Trojan Battery website (www.trojanBattery.com) for the most up-to-date information.